

# TECHNICAL DATA SHEET

**Material:** Recycled Black Injection Grade EPDM Modified PP Copolymer

**Reference:** A-85Q

**Attributes:**

- High impact copolymer
- High degree of toughness, strength and noise attenuation properties
- Good processability by injection moulding
- The impact properties are well preserved at low temperatures

**Packaging:**

A085Q - 25kg Paper Sacks	A385Q - Octaboxes
A185Q - 25kg Plastic Sacks	A485Q - Tanker
A285Q - Bulk Bags	

## Typical Values

Property	Test Method	Units	Average	Range
Ash Content	Internal	%	-	< 5
Density	ISO 1872/1 - 1986	kg/m <sup>3</sup>	930.00	908 - 955
Melt Flow Index	ISO 1133 - 230°C, 2.16kg	g/600secs	13.00	10 - 16
Moisture	Internal	%	-	< 0.1
Notched IZOD Impact Strength	ISO 180/1A, 23C	kJ/m <sup>2</sup>	-	> 12

LRS1412 - 0

Date Printed: 21/07/2011

Date Created: 21/07/2011

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designed cannot be assumed.