

TECHNICAL DATA SHEET

Material: Recycled Black Injection Grade Impact Modified PP Copolymer Compoun

Reference: A-85R

Attributes:

- A high impact copolymer formulated for a high degree of toughness, strength and noise attenuation properties.
- Good ease of moulding
- Excellent impact performance at low temperatures

Packaging:

A085R - 25kg Paper Sacks	A385R - Octaboxes
A185R - 25kg Plastic Sacks	A485R - Tanker
A285R - Bulk Bags	

Typical Values

Property	Test Method	Units	Average	Range
Ash Content	Internal	%	-	< 5
Density	ISO 1872/1 - 1986	kg/m ³	931.50	908 - 955
Melt Flow Index	ISO 1133 - 230°C, 2.16kg	g/600secs	12.00	10 - 14
Moisture	Internal	%	-	< 0.1
Notched IZOD Impact Strength	ISO 180/1A, -18°C	kJ/m ²	-	> 4
Notched IZOD Impact Strength	ISO 180/1A, 23C	kJ/m ²	-	> 15

LRS1411 - 0

Date Printed: 20/07/2011

Date Created: 20/07/2011

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designed cannot be assumed.

REGISTERED OFFICE: Allerton Bywater Business Park, Newton Lane, Allerton Bywater, Castleford, West Yorkshire, WF10 2AL

REGISTERED No: 07289595 - ENGLAND