

# TECHNICAL DATA SHEET

**Material:** Recycled Black Injection grade Talc filled PP Copolymer Compound

**Reference:** A-85T13

**Attributes:**

- Medium flow 13% talc reinforced copolymer
- Good ease of moulding
- Excellent balance between stiffness and impact performance
- Even and consistent appearance

**Packaging:** A085T13 - 25kg Paper Sacks                      A385T13 - Octaboxes  
A185T13 - 25kg Plastic Sacks                      A485T13 - Tanker  
A285T13 - Bulk Bags

## Typical Values

Property	Test Method	Units	Average	Range
Ash Content	Internal	%	13.00	11 - 15
Melt Flow Index	ISO 1133 - 230°C, 2.16kg	g/600secs	12.50	10 - 15
Moisture	Internal	%	-	< 0.1
Notched IZOD Impact Strength	ISO 180/1A, 23C	kJ/m2	-	> 4

LRS1415 - 0

Date Printed: 21/07/2011

Date Created: 21/07/2011

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designed cannot be assumed.

REGISTERED OFFICE: Allerton Bywater Business Park, Newton Lane, Allerton Bywater, Castleford, West Yorkshire, WF10 2AL

REGISTERED No: 07289595 - ENGLAND