

TECHNICAL DATA SHEET

Material: Recycled Black Talc Filled PP Copolymer Compound

Reference: A-85T40

Attributes:

- 40% Talc Reinforced Polymer
- Even and consistent appearance
- Good ease of moulding

Packaging:

A085T40 - 25kg Paper Sacks	A385T40 - Octaboxes
A185T40 - 25kg Plastic Sacks	A485T40 - Tanker
A285T40 - Bulk Bags	

Typical Values

Property	Test Method	Units	Average	Range
Ash Content	Internal	%	40.00	37 - 43
Melt Flow Index	ISO 1133 - 230°C, 2.16kg	g/600secs	12.00	9 - 15
Moisture	Internal	%	-	< 0.1
Notched IZOD Impact Strength	ISO 180/1A, 23C	kJ/m2	-	> 4

LRS1417 - 0

Date Printed: 21/07/2011

Date Created: 21/07/2011

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designed cannot be assumed.

REGISTERED OFFICE: Allerton Bywater Business Park, Newton Lane, Allerton Bywater, Castleford, West Yorkshire, WF10 2AL

REGISTERED No: 07289595 - ENGLAND