

TECHNICAL DATA SHEET

Material:	Recycled Black Injection Grade HDPE Compound		
Reference:	H-750		
Attributes:	<ul style="list-style-type: none">- Even and consistent appearance- Excellent balance between stiffness and impact performance- Good ease of moulding		
Packaging:	H0750 - 25kg Paper Sacks	H3750 - Octaboxes	
	H1750 - 25kg Plastic Sacks	H4750 - Tanker	
	H2750 - Bulk Bags		

Typical Values

Property	Test Method	Units	Average	Range
Density	ISO 1872/1 - 1986	kg/m ³	956.00	948 - 965
Melt Flow Index	ISO 1133 - 190°C, 2.16kg	g/600secs	5.00	3 - 7
Moisture	Internal	%	-	< 0.1
Notched IZOD Impact Strength	ISO 180/1A, 23C	kJ/m ²	-	> 4

LRS1419 - 0

Date Printed: 22/07/2011

Date Created: 22/07/2011

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designed cannot be assumed.

REGISTERED OFFICE: Allerton Bywater Business Park, Newton Lane, Allerton Bywater, Castleford, West Yorkshire, WF10 2AL

REGISTERED No: 07289595 - ENGLAND