

TECHNICAL DATA SHEET

Material: Recycled Black HIPS Compound

Reference: I-750

Attributes:

- Even and consistent appearance
- Suitable for Sheet Extrusion and Injection Moulding
- Excellent balance between stiffness and impact performance

Packaging:

I0750 - 25kg Paper Sacks	I3750 - Octaboxes
I1750 - 25kg Plastic Sacks	I4750 - Tanker
I2750 - Bulk Bags	

Typical Values

Property	Test Method	Units	Average	Range
Melt Flow Index	ISO 1133 - 200°C, 5kg	g/600secs	5.50	3 - 8
Moisture	Internal	%	-	< 0.1
Notched IZOD Impact Strength	ISO 180/1A, 23C	kJ/m ²	-	> 7

LRS1421 - 0

Date Printed: 22/07/2011

Date Created: 22/07/2011

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designed cannot be assumed.

REGISTERED OFFICE: Allerton Bywater Business Park, Newton Lane, Allerton Bywater, Castleford, West Yorkshire, WF10 2AL

REGISTERED No: 07289595 - ENGLAND